

Sample ID: H&N BARACUDA 18 5.52 MM**Sample Description****Date Sampled:**

Other form - rework required

SPECIFICATION: Pellet Lead

<u>ELEMENT/TEST</u>	<u>RESULT</u>	<u>Unit</u>	<u>MINIMUM</u>	<u>MAXIMUM</u>	<u>SF*</u>	<u>MU**</u>	<u>METHOD / TECHNOLOGY</u>
(Sn) Tin	0.002	% Weight				0.07	WI-01231, OES
(Pb) Lead	99.56	% Weight		Balance			Calculated as Balance
(As) Arsenic	<0.001	% Weight				0.001	WI-01231, OES
(Cu) Copper	0.003	% Weight				0.005	WI-01231, OES
(Bi) Bismuth	0.044	% Weight				0.002	WI-01231, OES
(Zn) Zinc	0.001	% Weight				0.002	WI-01231, OES
(Fe) Iron	<0.001	% Weight				0.0003	WI-01231, OES
(Ag) Silver	0.003	% Weight				0.016	WI-01231, OES
(Sb) Antimony	0.38	% Weight				0.07	WI-01231, OES
(Ni) Nickel	<0.001	% Weight				0.0008	WI-01231, OES
(Cd) Cadmium	0.001	% Weight				0.0009	WI-01231, OES
(Al) Aluminum	<0.001	% Weight				0.0002	WI-01231, OES
(Au) Gold	<0.001	% Weight				0.003	WI-01231, OES
(In) Indium	<0.001	% Weight				0.003	WI-01231, OES
(S) Sulfur	0.003	% Weight					WI-01231, OES
(P) Phosphorus	<0.001	% Weight					WI-01231, OES